





CLAIMS

1. A room-temperature molten salt comprising a mixture of two or more organic salts with different anionic moieties and different organic cationic moieties, the room-temperature molten salt having a solidifying point lower than that of any of the individual organic salts.

2. A room-temperature molten salt according to claim 1, wherein the two or more organic salts are selected from the group consisting of the organic salts represented by formulae (I), (II), (III) and (IV):



wherein R^{1a} to R^{5a} , R^{7a} , R^{9a} and R^{10a} are the same or different and each represents a hydrogen atom, a halogen atom, an alkyl group, a cycloalkyl group, a heterocyclic



group, a haloalkyl group, an aralkyl group, an aryl group,
an alkoxy group, an aryloxy group or an aralkyloxy group;
 R^{8a} is a hydrogen atom, an alkyl group, a cycloalkyl group,
a heterocyclic group, a haloalkyl group, an aralkyl group
5 or an aryl group; R^{6a} , R^{11a} , R^{12} , R^{13} , R^{14} , R^{15} , R^{16} , R^{17} , R^{18}
and R^{19} are the same or different and each represents an
alkyl group, a cycloalkyl group, a heterocyclic group, a
haloalkyl group, an aralkyl group or an aryl group; two
groups selected from the group consisting of R^{12} , R^{13} , R^{14}
10 and R^{15} may be linked at their ends to form, together with
the adjacent nitrogen atom, a nitrogen-containing
aliphatic heterocycle; two groups selected from the group
consisting of R^{16} , R^{17} , R^{18} and R^{19} may be linked at their
ends to form, together with the adjacent phosphorus atom,
15 a phosphorus-containing aliphatic heterocycle; and X_1^- ,
 X_2^- , X_3^- and X_4^- are each a conjugate base of a Brönsted
acid.

3. A room-temperature molten salt according to
claim 1 or 2, wherein at least one of the two or more
20 organic salts is a solid at room temperature.

4. A room-temperature molten salt according to
claim 1 or 2, wherein all of the two or more organic salts
are solids at room temperature.

5. A room-temperature molten salt according to
25 claim 1 or 2, wherein at least one of the two or more

organic salts is selected from the group consisting of the organic salts represented by formulae (V) and (VI):



5 wherein R^1 to R^5 , R^7 , R^9 and R^{10} are the same or different and each represents a hydrogen atom, a halogen atom, an alkyl group, a cycloalkyl group, a heterocyclic group, a haloalkyl group, an aralkyl group, an aryl group, an alkoxy group, an aryloxy group or an aralkyloxy group; R^8
 10 is a hydrogen atom, an alkyl group, a cycloalkyl group, a heterocyclic group, a haloalkyl group, an aralkyl group or an aryl group; R^6 and R^{11} are the same or different and each represents a C_{1-10} alkyl group in which at least one hydrogen atom is substituted by fluorine; and X_1^- and X_2^-
 15 are each a conjugate base of a Brönsted acid.

6. A room-temperature molten salt according to claim 5, wherein all of the two or more organic salts are selected from the group consisting of the organic salts represented by formulae (V) and (VI).

20 7. A room-temperature molten salt according to claim 5 or 6, wherein at least one of the two or more organic salts is a solid at room temperature.

8. A room-temperature molten salt according to claim 5 or 6, wherein all of the two or more organic salts are solids at room temperature.

9. A room-temperature molten salt according to
5 any one of claims 5 to 8, wherein, in formulae (V) and (VI), R^1 to R^5 , R^7 , R^9 and R^{10} are the same or different and each represents a hydrogen atom, a halogen atom, an alkyl group or a haloalkyl group; R^8 is an alkyl group; R^6 and R^{11} are the same or different and each represents a
10 group of the formula $-CH_2R^{12}$ wherein R^{12} is a straight- or branched-chain C_{1-9} alkyl group in which at least one hydrogen atom is substituted by fluorine.

10. A room-temperature molten salt according to claim 6, wherein all of the two or more organic salts are
15 selected from the group consisting of the organic salts represented by formula (V) and are solids at room temperature.

11. A room-temperature molten salt according to claim 6, wherein all of the two or more organic salts are
20 selected from the group consisting of the organic salts represented by formula (VI) and are solids at room temperature.

12. A room-temperature molten salt according to claim 6, wherein the two or more organic salts are at
25 least one organic salt that is selected from the group

consisting of the organic salts represented by formula (V) and is a solid at room temperature, and at least one organic salt that is selected from the group consisting of the organic salts represented by formula (VI) and is a solid at room temperature.

13. A room-temperature molten salt according to claim 6, wherein the two or more organic salts are two organic salts that are selected from the group consisting of the organic salts represented by formulae (V) and (VI) and are solids at room temperature; one of the organic salts having an anionic moiety represented by formula:



wherein Rf and Rf' are different and each represents a polyfluoroalkyl group, and

15 the other of the organic salts having an anionic moiety represented by the formula



wherein Rf'' is a polyfluoroalkyl group.

14. A room-temperature molten salt obtainable by mixing two or more organic salts with different anionic moiety and different organic cationic moieties, the room-temperature molten salt having a solidifying point lower than that of any of the individual organic salts.

15. A process for producing a room-temperature molten salt, comprising mixing two or more organic salts

with different anionic moieties and different cationic moieties, the room-temperature molten salt having a solidifying point lower than that of any of the individual organic salts.

5 16. A process according to claim 15, wherein the two or more organic salts are selected from the group consisting of the organic salts represented by formulae (I) to (IV).

10 17. A process according to claim 15 or 16, wherein at least one of the two or more organic salts is a solid at room temperature.

 18. A process according to claim 15 or 16, wherein all of the two or more organic salts are solids at room temperature.

15 19. A process according to claim 15, wherein the two or more organic salts are selected from the group consisting of the organic salts represented by formulae (V) and (VI) and are solids at room temperature.

20 20. An electrolytic solution comprising a room-temperature molten salt according to any one of claims 1 to 14.

 21. A battery comprising an electrolytic solution according to claim 20, a positive electrode, a negative electrode and a separator.

25 22. A battery according to claim 21, which is a

nonaqueous lithium secondary battery.

23. A solvent for use in organic reaction, comprising a room-temperature molten salt according to any one of claims 1 to 14.

5 24. An extraction solvent comprising a room-temperature molten salt according to any one of claims 1 to 14.

25. A capacitor comprising an electrolyte or electrolytic solution that comprises a room-temperature
10 molten salt according to any one of claims 1 to 14.

26. An electric double layer capacitor comprising an electrolyte or electrolytic solution that comprises a room-temperature molten salt according to any one of claims 1 to 14.

15 27. A dye-sensitized solar cell comprising a room-temperature molten salt according to any one of claims 1 to 14.

28. A fuel cell comprising a room-temperature molten salt according to any one of claims 1 to 14.

20 29. A polymer electrolyte fuel cell comprising a room-temperature molten salt according to any one of claims 1 to 14.